


15 cup

HOME
HELP

MASTER



OAK RIDGE NATIONAL LABORATORY
operated by
UNION CARBIDE CORPORATION
NUCLEAR DIVISION
for the
U.S. ATOMIC ENERGY COMMISSION



ORNL - TM - 2021, Vol. 1

RECEIVED BY DTIE MAY 8 1969

EFFECT OF ALLOYING ADDITIONS ON CORROSION BEHAVIOR OF NICKEL -
MOLYBDENUM ALLOYS IN FUSED FLUORIDE MIXTURES
(Thesis)
Jackson Harvey DeVan

This report is a portion of a thesis submitted to the Graduate Council of the University of Tennessee in partial fulfillment of the requirements for the degree of Master of Science.

LEGAL NOTICE

This report was prepared as an account of Government sponsored work. Neither the United States, nor the Commission, nor any person acting on behalf of the Commission:

- A. Makes any warranty or representation, expressed or implied, with respect to the accuracy, completeness, or usefulness of the information contained in this report, or that the use of any information, apparatus, method, or process disclosed in this report may not infringe privately owned rights; or
- B. Assumes any liabilities with respect to the use of, or for damages resulting from the use of any information, apparatus, method, or process disclosed in this report.

As used in the above, "person acting on behalf of the Commission" includes any employee or contractor of the Commission, or employee of such contractor, to the extent that such employee or contractor of the Commission, or employee of such contractor prepares, disseminates, or provides access to, any information pursuant to his employment or contract with the Commission, or his employment with such contractor.

LEGAL NOTICE

This report was prepared as an account of Government sponsored work. Neither the United States, nor the Commission, nor any person acting on behalf of the Commission:

A. Makes any warranty or representation, expressed or implied, with respect to the accuracy, completeness, or usefulness of the information contained in this report, or that the use of any information, apparatus, method, or process disclosed in this report may not infringe privately owned rights; or

B. Assumes any liabilities with respect to the use of, or for damages resulting from the use of any information, apparatus, method, or process disclosed in this report.

As used in the above, "person acting on behalf of the Commission" includes any employee or contractor of the Commission, or employee of such contractor, to the extent that such employee or contractor of the Commission, or employee of such contractor prepares, disseminates, or provides access to, any information pursuant to his employment or contract with the Commission, or his employment with such contractor.

ORNL-TM-2021
Vol. I

Contract No. W-7405-eng-26

METALS AND CERAMICS DIVISION

EFFECT OF ALLOYING ADDITIONS ON CORROSION BEHAVIOR OF NICKEL-
MOLYBDENUM ALLOYS IN FUSED FLUORIDE MIXTURES

Jackson Harvey DeVan

MAY 1969

This report is a portion of a thesis submitted to the Graduate Council of the University of Tennessee in partial fulfillment of the requirements for the degree of Master of Science.

OAK RIDGE NATIONAL LABORATORY
Oak Ridge, Tennessee
operated by
UNION CARBIDE CORPORATION
for the
U.S. ATOMIC ENERGY COMMISSION

1

2

3

4

5

CONTENTS

	Page
Abstract	1
Introduction	1
Review of Related Work	3
Corrosion by Fluoride Mixtures	3
Corrosion Reactions	3
Reduction of UF ₄ by Chromium	4
Corrosion of Nickel-Molybdenum Alloys.	6
Materials and Procedures	8
Test Materials	8
Test Equipment	8
Salt Preparation	12
Operating Procedures	13
Test Examination	13
Results and Discussion	15
Chromium	15
Corrosion-Product Concentrations	15
Metallographic Results	21
Aluminum	24
Corrosion-Product Concentrations	24
Metallographic Results	25
Titanium	28
Corrosion-Product Concentrations	28
Metallographic Results	29
Vanadium	30
Corrosion-Product Concentrations	30
Metallographic Results	30
Iron	30
Corrosion-Product Concentrations	30
Metallographic Results	32

	Page
Niobium	32
Corrosion-Product Concentrations	32
Metallographic Results	33
Tungsten	34
Corrosion-Product Concentrations	34
Metallographic Results	36
Relative Thermodynamic Stabilities of Alloying Constituents . .	36
General Discussion of Alloying Effects	38
Summary and Conclusions	40
Acknowledgments	42

EFFECT OF ALLOYING ADDITIONS ON CORROSION BEHAVIOR OF NICKEL-
MOLYBDENUM ALLOYS IN FUSED FLUORIDE MIXTURES

ABSTRACT

Fused fluoride mixtures containing UF_4 have been developed as fuel solutions for high-temperature nuclear reactors. To develop container materials for such mixtures, we investigated the corrosion properties of nickel-molybdenum alloys with various solid-solution strengthening additions. These evaluations utilized thermal convection loops which circulated salt mixtures between a hot-zone temperature of $815^\circ C$ and a cold-zone temperature of $650^\circ C$.

The alloys selected for study contained 17 to 20% Mo and various percentages of Cr, Al, Ti, V, Fe, Nb, and W. Loops of individual alloys were exposed to the salt mixture NaF-LiF-KF- UF_4 (11.2-45.3-41.0-2.5 mole %) for periods of 500 and 1000 hr. Measurements of the concentrations of corrosion products in after-test salt samples indicated the corrosion susceptibility of alloying additions to increase in this order: Fe, Nb, V, Cr, W, Ti, and Al. However, metallographic examinations of loop surfaces showed relatively light attack for all alloys except those containing combined additions of aluminum and titanium or aluminum and chromium.

A nickel-base alloy containing 17% Mo, 7% Cr, and 5% Fe, designated Hastelloy N, was found to afford the best combination of strength and corrosion resistance among the alloy compositions tested.

INTRODUCTION

Molten fluorides of uranium, thorium, or plutonium, in combination with other fluoride compounds, have wide applicability as fuels for the production of nuclear power.¹ Because of their high boiling points, these mixtures can be contained at low pressures even at extremely high operating temperatures. Their chemical and physical properties impart additional advantages such as excellent stability under irradiation and large

¹R. C. Briant and A. M. Weinberg, "Molten Fluorides as Power Reactor Fuels," Nucl. Sci. Eng. 2, 797-803 (1957).

solubility ranges for both uranium and thorium. These factors have prompted design studies of molten fluoride fuel systems in conjunction with thorium-uranium thermal breeders, uranium-plutonium converters, and uranium burners.

The development of reactors which incorporate a circulating fluoride salt is predicated on the availability of a construction material which will contain the salt over long time periods and also afford useful structural properties. The container material must also be resistant to air oxidation, be easily formed and welded into relatively complicated shapes, and be metallurgically stable over a wide temperature range.

In order to provide a material for initial reactor studies, several commercially available high-temperature alloy systems were evaluated with respect to the above requirements. As a result of these studies, Inconel, a nickel-base alloy containing 15 wt % Cr and 7 wt % Fe, was found to afford the best combination of desired properties and was utilized for the construction of the Aircraft Reactor Experiment.² Extensive corrosion tests,^{3,4} as well as posttest examinations of the ARE,⁵ confirmed the suitability of Inconel as a container material for relatively short-term fluoride salt exposures. Corrosion rates encountered with this alloy at temperatures above 700°C, however, were excessive for long-term use with most fluoride fuel systems.

Utilizing experience gained in corrosion testing of commercial alloys, we initiated an alloy development program to provide an advanced container material for fluoride fuel reactor systems. The reference alloy system was composed of nickel with a primary strengthening addition of 15-20% Mo. This composition afforded exceptional resistance to fluoride attack but lacked sufficient mechanical strength and oxidation

²W. D. Manly et al., Aircraft Reactor Experiment - Metallurgical Aspects, ORNL-2349 (1957).

³G. M. Adamson, R. S. Crouse, and W. D. Manly, Interim Report on Corrosion by Alkali-Metal Fluorides: Work to May 1, 1953, ORNL-2337 (1959).

⁴G. M. Adamson, R. S. Crouse, and W. D. Manly, Interim Report on Corrosion by Zirconium-Base Fluorides, ORNL-2338 (1961).

⁵W. B. Cottrell et al., Disassembly and Postoperative Examination of the Aircraft Reactor Experiment, ORNL-1868 (1958).

resistance at desired operating temperatures. To augment these latter properties, additions of various solid-solution alloying agents were evaluated, among them Cr, Al, Ti, Nb, Fe, V, and W. An optimum alloy composition was selected on the basis of parallel investigations of the mechanical and corrosion properties which were imparted by each of these additions. The composition best suited to reactor use was determined to be within the range 15-17 wt % Mo, 6-8 wt % Cr, 4-6 wt % Fe, 0.04-0.08 wt % C, balance Ni. Subsequent studies of the alloy, designated Hastelloy N, have shown it to be extremely well suited for applications demanding long-term compatibility with fluoride salts in the temperature range 650-800°C.

The present research was concerned with the corrosion effects resulting from additions of alloying elements to the nickel-molybdenum system and an analysis of the thermodynamics of the corrosion process as indicated by these alloying effects.


REVIEW OF RELATED WORK

Corrosion by Fluoride Mixtures

Corrosion Reactions

The corrosion of nickel-base alloys, containing iron and chromium, by fluoride fuel mixtures has been found to result from a combination of the following types of oxidation reactions:⁶


1. Reactions⁷ involving impurities in the salt



⁶W. D. Manly et al., "Metallurgical Problems in Molten Fluoride Systems," Progr. Nucl. Energy, Ser. IV 2, 164 (1960).


⁷Solid-solution alloying elements are underlined.

2. Reactions involving impurities in or on the metal, for example



followed by reaction (2).

3. Reactions involving components in the salt



The extent of the first four of these reactions, which proceed strongly to the right and to completion rapidly, can be reduced by maintaining low impurity concentrations in the salt and on the surface of the metal. Reactions (5) and (6), on the other hand, are indigenous to fluoride systems which derive their usefulness through the containment of UF_4 . While the role of chromium has been investigated extensively in connection with these reactions,⁸ considerably less information is available regarding the thermodynamics of these reactions for the other alloying elements which were of interest in the present study.

Reduction of UF_4 by Chromium


The reaction of UF_4 with chromium is found to be strongly influenced by the reaction medium employed.⁸ In melts composed principally of NaF-ZrF_4 or NaF-BeF_2 , the reaction produces only divalent chromium, that is,



However, in the case of NaF-KF-LiF-UF_4 mixtures used for this investigation, the reaction between chromium and UF_4 produces both divalent and

⁸J. D. Redman, ANP Quart. Progr. Rept. Dec. 31, 1957, ORNL-2440, pp. 78-82.

trivalent chromium. At equilibrium, approximately 80% of the total chromium ions in the mixtures are observed to be trivalent, giving the net reaction



The equilibrium constant for this reaction is given by

$$K_\alpha = \frac{(\alpha_{\text{CrF}_2})^{0.2} (\alpha_{\text{CrF}_3})^{0.8} (\alpha_{\text{UF}_3})^{2.8}}{(\alpha_{\text{UF}_4})^{2.8} (\alpha_{\underline{\text{Cr}}})} \quad (9)$$

where α represents thermodynamic activity. Because of the relatively small concentrations of CrF_2 and UF_3 which are attained in the salt solutions at equilibrium, the activities of each of these components can be closely approximated by their mole fractions, in accordance with Henry's law. Thus, for a salt system of fixed UF_4 concentration, assuming the reference states for salt components to be the infinitely dilute solution,

$$K_\alpha = \frac{(N_{\text{CrF}_2})^{0.2} (N_{\text{CrF}_3})^{0.8} (N_{\text{UF}_3})^{2.8}}{(\alpha_{\text{UF}_4})^{2.8} (\alpha_{\underline{\text{Cr}}})} \quad (10)$$

For a system initially containing no UF_3 , CrF_2 , or CrF_3 , it follows that $N_{\text{CrF}_2} = 1/4 N_{\text{CrF}_3} = 1/14 N_{\text{UF}_3}$. In such systems where the change in UF_4 concentration is small, Eq. (9) reduces to

$$(N_{\text{CrF}_2} + N_{\text{CrF}_3}) = K_N \alpha_{\underline{\text{Cr}}}^{5/19} \quad (11)$$

where

$$K_N = 5 \left(\frac{K_\alpha}{4} \right)^{4/19} \left(\frac{\alpha_{\text{UF}_4}}{14} \right)^{14/19}$$

The constant K_N has been experimentally determined for the mixture LiF-KF-NaF-UF₄ (11.2-41.0-45.3-2.5 mole %) by equilibrating it with pure chromium ($\alpha_{Cr}^{\circ} = 1$) at 600 and 800°C (ref. 8). Under these conditions, the constant is equivalent in value to the mole fraction of chromium ions in the salt at equilibrium. The measured values of K_N are listed in Table 1.

Table 1. Equilibrium Concentrations^a of Chromium Fluorides for the Reaction of Pure Chromium with UF₄

Equilibration Temperature (°C)	Concentration of Chromium Ions in NaF-LiF-KF-UF ₄ (11.2-41.0-45.3-2.5 mole %)	
	ppm	mole fraction (K_N)
600	1100	1.0×10^{-3}
800	2600	2.4×10^{-3}

^aJ. D. Redman, ANP Quart. Progr. Rept. Dec. 31, 1957, ORNL-2440, pp. 78-82.

Because the chromium-UF₄ reaction is temperature dependent, chemical equilibrium between these two components is precluded in systems of uniform alloy composition where the circulating salt continually experiences a temperature change. In such systems chromium tends to be continually removed from hotter portions and deposited in cooler portions. A theory relating the rate of this movement to the operating parameters of the container system has been formulated by Evans.⁹

Corrosion of Nickel-Molybdenum Alloys

Because of the oxidation of chromium by fuel-bearing fluoride salts, alloys employing large percentages of this element were not satisfactory

⁹R. B. Evans, ANP Quart. Progr. Rept. Dec. 31, 1957, ORNL-2440, pp. 104-113.

as container materials except at temperatures where diffusion rates in the alloys were relatively low. Accordingly, evaluations were made of several commercial alloys in which chromium was not employed as a major alloying addition. Based on these tests, alloys of nickel and molybdenum appeared to offer the most promising container system for achieving relatively high reactor operating temperatures. Unfortunately, commercially available nickel-molybdenum alloys which exhibited excellent corrosion properties were not well suited to contemplated reactor systems because of three adverse characteristics: (1) poor fabricability; (2) a tendency to age-harden and embrittle at service temperatures between 650 and 815°C (ref. 10); and (3) poor resistance to oxidation by air at elevated temperatures. The scale formed on exposure of these alloys to high-temperature air was of the type NiMoO_4 , which upon thermal cycling between 760 and 350°C underwent a phase transformation and spalled as a consequence of a resultant volume change.¹¹

By means of an alloy development program, however, it was considered plausible to eliminate the undesirable features of the commercial materials while retaining their inherent corrosion resistance. The initial objective of this program was to provide an alloy which did not embrittle under the thermal treatments imposed by reactor operation. By experimenting with various compositions of binary nickel-molybdenum alloys, it was determined that lowering the molybdenum concentration to a level of 15-17% served to avoid detrimental age-hardening effects in the alloy system.¹² Although such an alloy system was satisfactory from the standpoint of corrosion resistance, it was necessary to augment the oxidation and strength characteristics of the system through additional solid-solution alloying agents. The corrosion effects which resulted from these additions were the subjects of the present study.

¹⁰R. E. Clausing, P. Patriarca, and W. D. Manly, Aging Characteristics of Hastelloy B, ORNL-2314 (1957).

¹¹H. Inouye, private communication.

¹²D. W. Stoffel and E. E. Stansbury, "A Metallographic and X-ray Study of Ni Alloys of 20-30 Per Cent Mo," Report No. 1 under Subcontract No. 582 under Contract No. W-7405-eng-26, Knoxville, Tenn., Dept. of Chem. Eng. of the Univ. of Tenn. (1955).

MATERIALS AND PROCEDURES

Test Materials

The nickel-molybdenum alloy compositions selected for study were supplied by the Metals and Ceramics Division at ORNL and, under subcontract agreements, by Battelle Memorial Institute and Superior Tube Company. Alloys furnished by ORNL were induction-melted under vacuum, while those furnished by subcontractors were induction-melted in air using a protective slag. Each alloy heat, which ranged in weight from 12 to 100 lb, was either forged or extruded into a 3-in.-diam tube blank and was subsequently drawn into 1/2-in.-OD seamless tubing by the Superior Tube Company. The cold-drawn tubing was annealed at 1120°C. Table 2 lists the experimental alloy compositions used for this corrosion study.

Test Equipment

The method selected to evaluate the corrosion properties of these alloys was based on the following considerations:

1. The method necessarily had to be tailored to the use of relatively small quantities of material, since it was practical to produce only small heats of the many alloys desired for study.
2. Tubing was considered to be a highly desirable form in which to test the material, since production of the material in this form was carried out as an adjunct to evaluating the fabricability of each alloy.
3. Previous demonstrations of the effects of temperature gradient in the salt and the salt flow rate on the corrosion behavior of container materials in fluorides made it mandatory that corrosion tests be conducted under dynamic conditions, that is, conditions which provided for the continuous flow of salt through a temperature gradient.

The thermal convection loop, which had been used extensively for Inconel corrosion studies and had been developed into an extremely straightforward and reliable test device, was judged to be the best form of experimental device for meeting these requirements. This device consists of a closed loop of tubing, bent to resemble the outline of a harp,

Table 2. Compositions of Experimental Alloys Used for Corrosion Studies

Heat Number ^a	Composition, wt %										Composition, at. %								
	Ni	Mo	Cr	Fe	Ti	Al	Nb	W	V		Ni	Mo	Cr	Fe	Ti	Al	Nb	W	V
<u>Series I</u>																			
OR 30-1	80.12	16.93	2.83								85.50	11.10	3.41						
-2	78.55	16.65	4.62								83.60	10.80	5.55						
-4	73.65	16.37	9.21								78.30	10.60	11.04						
-6	78.50	15.11	6.40								82.70	9.72	7.60						
37A-1	77.0	20.39	2.62								83.30	13.50	3.20						
43A-3	73.30	20.34	6.34								78.90	13.40	7.71						
<u>Series II</u>																			
OR 30-7	82.10	15.93				1.88					85.60	10.15			4.26				
-8	80.30	17.80			1.89						85.90	11.60		2.47					
-9	81.10	16.8						2.09			88.10	11.20					0.72		
-10	81.10	16.60							2.23		86.40	10.80							2.73
-11	79.80	16.53		3.68							85.10	10.80		4.12					
-12	80.00	16.80					3.22				86.70	11.10					2.20		
-19	79.00	16.90						4.10			87.10	11.40						1.44	
-20	79.20	16.60							4.18		84.10	10.80							5.11
-21	78.90	16.40							4.71		85.50	10.90					3.62		
S T23012	82.00	17.42				0.53					87.40	11.40			1.22				
OR 1491	86.58	11.23				2.19					88.16	6.99			4.85				
<u>Series III</u>																			
OR 30-13	79.93	17.56			1.56	0.95					84.48	11.35		2.02	2.18				
-14	79.53	16.50			1.52	2.45					82.11	10.42		1.92	5.51				
-16	77.74	16.00	3.65		1.49	1.12					81.01	10.20	4.30	1.90	2.54				
-22	77.65	15.90	5.69			1.16	0.60				80.27	10.05	6.64		2.61	0.39			
-33	74.07	15.15	5.01	5.07		0.70					77.26	9.66	5.90	5.56	1.59				
B2897	76.13	20.50			1.25		1.32				83.61	13.77		1.68		0.92			
B2898	76.30	20.50			2.44		1.31				82.60	13.20		3.24		0.90			
B3276	69.19	21.10	7.58				2.16				75.17	14.00	9.32			1.48			
B3277	66.95	21.60	7.82			1.31	2.32				71.72	14.20	9.47		3.06	1.57			
S T23011	71.50	15.06	3.84			0.53	4.17	4.90			79.04	10.20	4.79		1.27	2.91	1.72		
S T23013	74.42	15.20				0.58	4.57	5.23			83.14	10.36			1.40	3.23	1.85		
S T23014	80.86	16.70			2.10	0.57					85.22	10.76		2.71	1.30				

^aOR denotes heats furnished by the Metals and Ceramics Division; S T by Superior Tube Company; and B by Battelle Memorial Institute.

two legs of which are heated and two of which are exposed to the cooling effects of ambient air. Flow results from the difference in density of the salt in the hot and cold portions of the loop.

The configuration and dimensions of the loop design are presented in Fig. 1. All loops were fabricated of seamless tubing having an outside diameter of 0.500 in. and a wall thickness of 0.035 in. The tubing was assembled by the Heliarc welding technique using an inert gas backing.

During operation the loops were heated by a series of clamshell resistance heating elements located as shown in Fig. 1. To fill the loop required that we apply heat to both the cold- and hot-leg sections. Auxiliary heating for this purpose was provided by passage of electric current directly through the tube wall. When the loop was filled, as determined by an electrical shorting probe near the top of the loop, the auxiliary heat source was turned off and the heating elements were turned on. Insulation was then removed from the cold leg to whatever amount was required to establish a predetermined temperature gradient.

Loop temperatures were measured with Chromel-P-Alumel thermocouples located as shown in Fig. 1. The thermocouple junctions, in the form of small beads, were welded to the outside tube wall with a condenser discharge welder and covered by a layer of quartz tape, which in turn was covered with stainless steel shim stock. All tests were operated so as to achieve a maximum mixed-mean salt temperature of 815°C and a minimum salt temperature of 650°C. The maximum salt-metal interface temperature, which was attained near the top of the vertical heated section, exceeded the maximum bulk salt temperature by approximately 95°C (ref. 13). The salt-flow rate under these temperature conditions was established from heat balance calculations to be in the range of 5 to 7 ft/min.

¹³Measurements of the maximum inside wall temperature could not practically be made in each loop test; however, values of this temperature were recorded by means of heat balance calculations and imbedded thermocouples using a specially instrumented test loop which exactly simulated the geometry and temperature profile used in the corrosion experiment.




Fig. 1. Schematic Diagram of Thermal Convection Loop Used for Evaluations of Experimental Nickel-Molybdenum Alloys. The locations of thermocouples and test samples are shown.

Salt Preparation

The fuel mixture used in these studies was of the composition shown in Table 3. We selected the LiF-KF-NaF-UF₄ composition (Salt 107) on the basis that the oxidation of container constituents by a given concentration of UF₄ tended to be greater for this mixture than for other mixtures of practical importance. Thus, achievement of satisfactory compatibility with this mixture in effect provided a container material of ultimate versatility with respect to all fuel mixtures.

Table 3. Composition of Fluoride Mixture
Used to Evaluate Experimental
Nickel-Molybdenum Alloys

Salt Number: 107
Liquidus Temperature: 490°C

Component	Mole %	Weight %
NaF	11.2	9.79
LiF	45.3	24.4
KF	41.0	49.4
UF ₄	2.5	16.3

The fluoride mixtures were prepared from reagent-grade materials and were purified by the Fluoride Processing Group of the Reactor Chemistry Division. In general, the procedure for purification was as follows: (1) the dry ingredients, except for UF₄, were mixed, evacuated several times for moisture removal, and then melted under an atmosphere of helium; (2) the molten mixture was held at 815°C and treated with hydrogen for 4 hr to purge hydrofluoric acid from the mixture; (3) the mixture was cooled to 205°C under a helium atmosphere and UF₄ was admitted. Upon the addition of the UF₄, the mixture was remelted, heated to 815°C, and then treated again with hydrogen to purge the excess hydrofluoric acid.

All mixtures were prepared in 300-lb quantities and apportioned into 50-lb containers, after which samples were submitted for analysis of Ni, Fe, and Cr. It was required that each of these elements be present

in amounts less than 500 ppm as determined from individual batch analyses. A second before-test analysis of each salt mixture was obtained from a sample of the salt taken as it was being admitted to the test loop.

Operating Procedures

Each loop was thoroughly degreased with acetone and checked for leaks using a helium mass spectrometer. After thermocouples and heaters were assembled and insulation was applied, the loop was placed in a test stand, as shown in Fig. 2.

The salt charging pot was connected to the loop with nickel or Inconel tubing, and both the loop and the charging pot were heated to 650°C under a dynamic vacuum of less than 50 μ Hg. Helium pressure was then applied to the charging pot in order to force the salt mixture from the pot to the loop. After filling, salt was allowed to stand in the loop at 650°C for approximately 2 hr, so that oxides and other impurities would be dissolved from the container surface into the salt mixture. This mixture was then removed, and a fresh salt mixture was admitted from the fluoride charging pot. A helium cover gas under slight positive pressure (approx 5 psig) was maintained over the salt mixture during all periods of testing.

At the end of test, power to the loop was cut off and insulation was stripped from the loop so as to freeze the salt mixture as rapidly as possible.

Test Examination

Each loop was sectioned with a tubing cutter into approximately 6-in. lengths. Five 2-in. sections were then removed from the loop positions indicated in Fig. 1 for metallographic examination. Two of the remaining 6-in. sections, one from the hottest section of the loop (specimen H) and one from the coldest section (specimen C), were obtained for salt chemistry studies, and the remaining loop segments were held in storage until all examinations of the loop were completed.

Salt removal was accomplished by heating each section in a small tube furnace at 600°C in helium. The salt was collected in a graphite

Photo 21341




Fig. 2. Photograph of Assembled Thermal Convection Loops and Test Stands.

crucible located below the furnace windings. The five 2-in. sections of tubing were examined metallographically, and the salt samples were submitted individually for petrographic and chemical analyses. If layers of corrosion products were discovered on the tube wall, samples of the tubing and salt contained in that section were also submitted for x-ray diffraction examination.

RESULTS AND DISCUSSION

Alloying effects were evaluated in terms of both the corrosion products entering the salt mixtures and the metallographic appearance of the alloy after test. Results have been grouped in this section according to the alloying element studied.

Chromium

Corrosion-Product Concentrations

Effects of chromium additions were examined in six ternary alloys with chromium contents of 3.2 to 11.0 at. %. One loop of each of these compositions was operated with Salt 107 for 500 hr under the test conditions described above. The compositions investigated and the attendant concentrations of chromium ions in salt samples taken at the conclusion of these tests are shown in Table 4. The extent of reaction between chromium and fluoride constituents, as indicated by the chromium ion concentrations, increased with the amount of chromium in the alloy. This increase is illustrated graphically in Fig. 3, where the data are compared with data for Inconel¹⁴ and for pure chromium.¹⁵ It may be noted that the chromium concentrations of the salts were less than those for Inconel loops operated under identical temperature conditions. A horizontal line, which represents the chromium ion concentration at

¹⁴G. M. Adamson, R. S. Crouse, and W. D. Manly, Interim Report on Corrosion by Alkali-Metal Fluorides: Work to May 1, 1953, ORNL-2337 (1959).

¹⁵J. D. Redman, ANP Quart. Progr. Rept. Dec. 31, 1957, ORNL-2440, pp. 78-82.

Table 4. Corrosion-Product Concentrations of Salts Tested with Nickel-Molybdenum-Chromium Alloys

Heat Number	Alloy Composition (at. %)		Test Duration (hr)	Chromium Concentration in Salt Samples ^a (mole %)		
	Cr	Other Components		Sample H	Sample C	Other
OR 37A-1	3.20	13.5 Mo, bal Ni	500	0.0194	0.0180	0.0213
OR 30-1	3.41	11.1 Mo, bal Ni	500	0.0222	0.0365	0.0291
OR 30-2	5.55	10.8 Mo, bal Ni	500	0.0375	0.0352	0.0376
OR 30-2	5.55	10.8 Mo, bal Ni	1000	0.0509	0.0509	0.0543
OR 30-6	7.60	9.72 Mo, bal Ni	500	0.0606	0.0606	0.0566
OR 43A-3	7.71	13.4 Mo, bal Ni	500	0.0453	0.0476	0.0425
OR 30-4	11.04	10.6 Mo, bal Ni	500	0.0819	0.0814	0.0699

^aSample designations "H" and "C" are discussed on page 13; "other" designates salt samples obtained from metallographic specimens.

equilibrium with pure chromium at 600°C, is seen in Fig. 3 to be above the measured chromium ion concentrations for all alloys tested. Thus, the observed concentrations were less than those required for the formation of pure chromium crystals in the coldest portion of the loops (approx 650°C).

As discussed previously, the concentration of chromium ions under the conditions of these tests should be governed by the relation [Eq. (11)]

$$N_{\text{Cr ions}} = (N_{\text{CrF}_2} + N_{\text{CrF}_3}) = K_2 \alpha_{\text{Cr}}^{5/19},$$

where $N_{\text{Cr ions}}$ is the mole fraction of chromium ions in Salt 107 at equilibrium with an alloy of given chromium activity, α_{Cr} . If we assume that N_{Cr} gives an approximate measure of α_{Cr} , the resultant chromium ion concentrations for these alloys should lie within a region which is bounded above by the function determined at a temperature equivalent to the maximum loop temperature and below by the function determined at the minimum loop temperature. Bounds using experimental values of K_2




Fig. 3. Concentration of Chromium Ions in Salt 107 as a Function of Chromium Content in Nickel-Molybdenum-Chromium Alloys.

measured at 800 and 600°C (Table 1), which reasonably approximate the maximum and minimum loop temperatures, are plotted in Fig. 3 and are seen to include only two of the observed loop concentrations, both corresponding to chromium compositions greater than 7 at. %. However, except for the alloy with least chromium content, all concentrations lie relatively close to the lower bound and roughly approximate the slope of this bound.

The deviation of measured corrosion-product concentrations in these tests from the predicted concentration ranges may have resulted primarily from inaccuracy in the assumption that N_{Cr} equals α_{Cr} . However, assuming α_{Cr} to be accurately known, the corrosion-product concentrations in these tests would nevertheless have been lower than those predicted, since corrosive attack would necessarily reduce the chromium content and hence the

chromium activity at the surface of the alloys relative to the original chromium activity. We also examined the possibility that the test times were not sufficiently long for the chromium concentration of the salt to have completely attained the maximum or steady-state level. To evaluate this latter point, sufficient material of one of the alloy compositions, heat OR 30-2, was obtained to permit the operation of a 1000-hr test. Results of this test, which are shown in Table 4 and Fig. 3, indicated that only a small increase in chromium concentration occurred between the 500- and 1000-hr intervals. It was concluded, therefore, that the 500-hr test provided a reasonably close estimate of the limiting corrosion-product concentrations associated with the temperature conditions of these experiments.

Additional data on the effects of chromium in nickel-molybdenum alloys were afforded by tests of five alloys which contained chromium in combination with one or more other alloying elements, as shown in Table 5. Notwithstanding the additional alloying agents, the concentrations of chromium-containing corrosion products following 500-hr tests of these alloys in Salt 107, as shown in Table 5, were comparable to the concentrations associated with the simple ternary chromium-containing alloys. The corrosion-product concentrations for the alloys with multiple additions are plotted in Fig. 4, and are seen to show the same general variation with chromium content as the ternary alloys (see Fig. 3).

Also shown in Table 5 and Fig. 4 are the results of 1000-hr tests of four of the alloys containing multiple additions. After all but one of these tests, the chromium ion concentrations in the salts were slightly higher than for 500-hr tests of the same alloys; in one test, the chromium ion concentration was unaccountably lower. The chromium ion concentrations of these multicomponent alloys again fell near those predicted on the basis of equilibrium data for pure chromium at 600°C and were considerably less than the concentration needed to deposit pure chromium at 600°C.

The chromium activities in all of the alloys tested would appear on the basis of corresponding corrosion-product concentrations to be lower than the activity of chromium in Inconel. However, it is important to note in Figs. 3 or 4 that any alloy in which the chromium activity

Table 5. Corrosion-Product Concentrations of Salts Tested with Nickel-Molybdenum Alloys Containing Chromium in Combination with Other Alloying Elements

Heat Number	Alloy Composition, at. %		Test Duration (hr)	Chromium Concentration in Salt Samples, ^a mole %		
	Chromium	Other Components		Sample H	Sample C	Other
OR 30-16	4.30	2.54 Al, 1.90 Ti, 10.2 Mo, bal Ni	500	0.0227	0.0236	0.0204
S T23011	4.79	1.27 Al, 2.91 Nb, 1.72 W, 10.2 Mo, bal Ni	500	0.0490	0.0490	0.0426
OR 30-33	5.90	1.59 Al, 5.56 Fe, 9.66 Mo, bal Ni	1000	0.0689	0.0731	0.0620
OR 30-22	6.64	0.43 Fe, 0.39 Nb, 2.61 Al, 10.05 Mo, bal Ni	500	0.0583	0.0555	0.0490
OR 30-22	6.64	0.43 Fe, 0.39 Nb, 2.61 Al, 10.05 Mo, bal Ni	1000	0.0416	0.0402	0.0370
B3276	9.32	1.48 Nb, 14.0 Mo, bal Ni	500	0.0615	0.0615	0.0578
B3277	9.47	1.57 Nb, 3.06 Al, 14.2 Mo, bal Ni	500	0.0698	0.0700	0.0624
B3277	9.47	1.57 Nb, 3.06 Al, 14.2 Mo, bal Ni	1000	0.0731	0.0657	0.0740

^aSample designations "H" and "C" are discussed on page 13; "other" designates samples obtained from metallographic specimens.




Fig. 4. Concentration of Chromium Ions in Salt 107 as a Function of Chromium Contents in Nickel-Molybdenum Alloys Containing Multiple Alloy Additions.

exceeded a value of 0.035 would support the formation of pure chromium at 600°C in any case where the concentration of CrF_2 and CrF_3 approached equilibrium with the alloy at temperatures of 800°C or above. Thus, unless the activity coefficients for chromium in these alloys are much smaller than unity, the possibility for the deposition of pure chromium in cold-leg regions cannot be completely excluded for any of the alloys tested.

In the case of ZrF_4 - or BeF_2 -base salt mixtures, the temperature dependence of the Cr-Uf_4 reaction is much less than for Salt 107. It has been shown¹⁶ that in these mixtures, alloys having a chromium

¹⁶W. R. Grimes, ANP Quart. Progr. Rept. March 10, 1956, ORNL-2106, pp. 96-99.

activity equivalent to or less than that for Inconel cannot support chromium ion concentrations at 800°C which are sufficiently high to maintain pure chromium at 600°C. Consequently, mass transfer of chromium by deposition of pure chromium crystals in the latter salt mixtures should not be possible for any of the alloys listed in Tables 4 and 5.

Metallographic Results

Metallographic examinations of the ternary alloys shown in Table 4 showed little evidence of corrosive attack other than shallow surface roughening. Void formation, which characteristically had been found in nickel-chromium alloys under similar test conditions,¹⁷ was not detected in any of these alloys. The relative depths of attack which occurred for the alloy containing 5.55 at. % Cr (heat OR 30-2) after 500- and 1000-hr tests, respectively, are compared in Fig. 5. Although the depth of attack was similar at both time intervals, the intensity of surface pitting was somewhat greater after the 1000-hr exposure. The intensity of surface roughening was also found to increase with increasing chromium concentration. This is seen in Fig. 6 which compares photomicrographs of two alloys containing different chromium contents. Cold-leg sections of these loops showed no evidence of corrosion and contained no visible deposits of corrosion products.

The depths of attack observed metallographically for alloys containing chromium in combination with other additions are shown graphically in Fig. 7. Attack in these alloys was manifested as surface roughening after 500 hr and as a combination of surface pitting and shallow void formation after 1000 hr. Depths of corrosion were in general higher than for the ternary chromium-containing alloys, particularly in alloys which contained aluminum additions.

¹⁷L. S. Richardson, D. C. Vreeland, and W. D. Manly, Corrosion by Molten Fluorides, ORNL-1491 (Sept. 1952).




Fig. 5. Appearance of Hot-Leg Surface of Ternary Nickel-Molybdenum Alloy Containing 5.55 at. % Cr Following Exposure to Salt 107. Heat OR 30-2. (a) After 500 hr and (b) after 1000 hr.




Fig. 6. Hot-Leg Sections of Nickel-Molybdenum-Chromium Thermal Convection Loops Following 500-hr Exposure to Salt 107. (a) 3.2 Cr-13.5 Mo-bal Ni (at. %), (b) 11.0 Cr-10.6 Mo-bal Ni (at. %).




Fig. 7. Depths of Corrosion Observed for Nickel-Molybdenum Alloys with Multiple Alloy Additions Following Exposure to Salt 107. Bars designating corrosion depths appear directly above the alloy compositions which they represent. (Where bars have both positively sloped and negatively sloped cross-hatching, the height of positively sloped cross-hatching indicates depth of corrosion after 500 hr and combined height of both types indicates depth after 1000 hr.)

Aluminum

Corrosion-Product Concentrations

Table 6 lists the concentrations of aluminum which were analytically determined in fluoride mixtures operated for 500- and 1000-hr periods with nickel-molybdenum alloys containing single additions of aluminum. In the case of alloys containing greater than 2 at. % Al, the corresponding aluminum concentrations in the salt mixture were relatively high, that is, in the range of 0.15–0.37 mole %. Only one alloy composition was subjected to tests at both 500 and 1000 hr; however, results for this alloy suggest that effectively similar salt concentrations were

Table 6. Corrosion-Product Concentrations of Salts Tested with Nickel-Molybdenum-Aluminum Alloys

Heat Number	Alloy Composition (at. %)		Test Duration (hr)	Aluminum Concentration in Salt Samples ^a (mole %)		
	Al	Other Components		Sample H	Sample C	Other
S T23012	1.22	11.4 Mo, bal Ni	500	0.000872	0.000872	b
OR 30-7	4.26	10.15 Mo, bal Ni	500	0.220	0.070	0.137
OR 30-7	4.26	10.15 Mo, bal Ni	1000	0.214	0.105	0.178
OR 1491	4.85	6.99 Mo, bal Ni	1000	0.374	0.374	0.374

^aSample designations "H" and "C" are discussed on page 13; "other" designates samples obtained from metallographic specimens.

^bNot determined.

realized for both time intervals. Table 7 lists the concentrations of corrosion products which formed in salt mixtures circulated in loops containing aluminum in combination with other alloying elements. These concentrations were of the same general magnitudes as those observed for the ternary Ni-Mo-Al alloys.

The corrosion-product concentrations showed no definable correspondence with the aluminum content of the alloys. However, the propensity for aluminum to react with interstitial contaminants, such as nitrogen, in these alloys, makes the activity of aluminum in the alloys very dependent on composition and metallurgical history. For this reason poor correspondence between the corrosion-product concentration and total aluminum concentration in the alloy would not be unexpected.

It is apparent from tests of both the ternary and multicomponent alloys that aluminum additions less than 2 at. % give rise to very much lower aluminum ion concentrations than additions above 2 at. %. This observation may suggest that below a concentration of 2 at. % the bulk of the aluminum addition has formed highly stable compounds with interstitial contaminants in the alloy.

Metallographic Results

Hot-leg surfaces of ternary alloys containing aluminum in amounts greater than 2 at. % underwent relatively severe attack by Salt 107 in

Table 7. Corrosion-Product Concentrations of Salts Tested with Nickel-Molybdenum Alloys Containing Aluminum in Combination with Other Alloying Elements

Heat Number	Alloy Composition, at. %		Test Duration (hr)	Aluminum Concentration of Salt Samples, ^a mole %		
	Aluminum	Other Components		Sample H	Sample C	Other
S T23014	1.30	10.8 Mo, 2.7 Ti, bal Ni	500	<0.0009	<0.0009	<0.0009
S T23013	1.40	10.4 Mo, 3.2 Nb, 1.8 W, bal Ni	500	0.160	0.0606	b
OR 30-33	1.59	9.7 Mo, 5.9 Cr, 5.6 Fe, bal Ni	1000	0.0660	0.0820	0.124
OR 30-16	2.54	10.2 Mo, 4.3 Cr, 1.9 Ti, bal Ni	500	0.358	0.326	0.334
OR 30-22	2.61	10.0 Mo, 6.6 Cr, 0.4 Fe, 0.4 Nb, 2.6 W, bal Ni	500	0.382	0.570	0.244
OR 30-22	2.61	10.0 Mo, 6.6 Cr, 0.4 Fe, 0.4 Nb, 2.6 W, bal Ni	1000	0.249	0.259	b
B3277	3.06	14.2 Mo, 9.5 Cr, 1.6 Nb, 3.1 W, bal Ni	500	0.502	0.525	0.481
B3277	3.06	14.2 Mo, 9.5 Cr, 1.6 Nb, 3.1 W, bal Ni	1000	0.473	0.394	0.374
OR 30-14	5.51	10.4 Mo, 1.9 Ti, bal Ni	500	0.394	0.439	0.499
OR 30-14	5.51	10.4 Mo, 1.9 Ti, bal Ni	1000	0.250	0.174	0.0960

^aSample designations "H" and "C" are discussed on page 13; "other" designates samples obtained from metallographic specimens.

^bNot determined.

the form of surface pitting and subsurface void formation. Void formation was evident to a depth of 0.002 in. in 500-hr tests of these alloys and to 0.003 in. in 1000-hr tests. Figure 8 shows the appearance of an alloy containing 4.27 at. % Al after a 1000-hr test exposure. However, an alloy containing only 1.22 at. % Al revealed negligible attack after a 500-hr exposure to Salt 107.

Alloys containing aluminum combined with other alloying components also exhibited both surface pitting and subsurface void formation after exposure to Salt 107. The depths of attack for these alloys are shown graphically in Fig. 7. Additions of up to 2 at. % Al resulted in only light attack except in alloys where chromium additions were also present. Alloys which contained over 2.5 at. % Al in combination with chromium or titanium revealed pronounced attack in the form of subsurface voids to depths ranging from 0.002 to 0.0045 in. Cold-leg sections of all loops were unattacked and contained no insoluble corrosion products.




Fig. 8. Hot-Leg Surface of Ternary Nickel-Molybdenum Alloy Containing 4.27 at. % Al After 1000-hr Exposure to Salt 107. Heat OR 30-7.

Titanium

Corrosion-Product Concentrations

Titanium-containing alloys which were investigated are listed in Table 8, together with attendant titanium corrosion-product concentrations. Except for the first composition shown, which contained 2.47 at. % Ti, alloying agents in addition to titanium were present in all of the alloys evaluated. The corrosion properties of the single ternary alloy were studied at both 500- and 1000-hr time intervals. Analyses of salts operated in loops of this alloy revealed titanium

Table 8. Corrosion-Product Concentrations of Salts Tested with Nickel-Molybdenum Alloys Containing Titanium

Heat Number	Alloy Composition (at. %)		Test Duration (hr)	Titanium Concentration in Salt Samples ^a (mole %)		
	Ti	Other Components		Sample H	Sample C	Other
OR 30-8	2.47	11.6 Mo, bal Ni	500	0.0394	0.0386	0.0380
OR 30-8	2.47	11.6 Mo, bal Ni	1000	0.0404	0.0495	0.0505
B2897	1.68	13.8 Mo, 0.9 Nb, bal Ni	1000	0.0373	0.0383	0.0283
OR 30-16	1.90	10.2 Mo, 4.3 Cr, 2.5 Al, bal Ni	500	0.0378	0.0348	0.0500
OR 30-14	1.92	10.4 Mo, 5.5 Al, bal Ni	500	0.0449	0.0489	0.0378
OR 30-14	1.92	10.4 Mo, 5.5 Al, bal Ni	1000	0.0373	0.0530	0.0434
OR 30-13	2.02	11.3 Mo, 2.2 Al, bal Ni	500	0.0389	0.0404	0.0484
S T23014	2.71	10.8 Mo, 1.3 Al, bal Ni	500	0.0187	0.0242	0.0187
B2898	3.24	13.2 Mo, 0.9 Nb, bal Ni	500	0.0353	0.0252	b

^aSample designation "H" and "C" are discussed on page 13; "other" designates samples obtained from metallographic specimens.

^bNot determined.

concentrations of 0.038-0.040 mole % after 500 hr and 0.040-0.055 mole % after 1000 hr. These analyses correspond closely to the analyses of salts circulated in loops constructed of the other titanium-bearing alloys, in which titanium contents ranged from 1.68-3.24 at. %. Only the test of the 2.71 at. % alloy effected a titanium salt concentration significantly different from the ternary alloy, the concentration in the former test being unaccountably lower than for the other tests.

Metallographic Results

The ternary titanium-bearing alloy revealed only light attack in the form of surface pitting after both the 500- and 1000-hr test intervals. The photomicrograph in Fig. 9 shows the appearance of a typical hot-leg section of this alloy after the longer test interval. Depths of attack which were observed in the remainder of the titanium-bearing alloys are graphically depicted in Fig. 7. Except where aluminum additions were present in these alloys in amounts greater than 2 at. %, depths of attack were in all cases less than 0.003 in. and generally




Fig. 9. Hot-Leg Surface of Ternary Nickel-Molybdenum Alloy Containing 2.47 at. % Ti After 1000-hr Exposure to Salt 107. Heat OR 30-8.

were less than 0.002 in. Attack in all cases was manifested as general surface pitting and shallow void formation. No attack was seen in the cold-leg sections of any of the titanium-containing loops nor were cold-leg deposits detected.

Vanadium

Corrosion-Product Concentrations

Loops were operated with two ternary alloys containing vanadium additions of 2.73 and 5.11 at. %, respectively. As shown in Table 9, the vanadium concentration detected in a salt mixture tested with the former alloy after 500-hr exposure was less than 0.005 mole %. However, salts operated with the alloy of higher vanadium content contained 0.027 mole % V in a 500-hr test and 0.019-0.020 mole % V in a 1000-hr test.

Metallographic Results

Metallographic examination of the alloy with 2.73 at. % V revealed very light attack in the form of surface roughening. Hot-leg surfaces of the alloy with 5.11 at. % V exhibited attack in the form of void formation to a depth of 0.002 in. in the 500-hr loop and 0.004 in. in the 1000-hr loop. A photomicrograph illustrating attack incurred by the latter loop is shown in Fig. 10.

Iron

Corrosion-Product Concentrations

Only two loop tests were completed with alloys containing iron as a major addition. Results of both tests, one of which operated for 500 hr and the other for 1000 hr, are summarized in Table 9. In the 500-hr loop, which contained 4.12 at. % Fe, after-test salt samples were analyzed to contain 0.013-0.015 mole % Fe. In the 1000-hr loop, which contained 5.56 at. % Fe together with aluminum and chromium additions, the after-test salt samples contained an even lower iron concentration. It would appear that corrosion products formed by reactions involving

Table 9. Corrosion-Product Concentrations of Salts Tested with Nickel-Molybdenum Alloys Containing Vanadium and Iron

Heat Number	Alloy Composition (at. %)						Test Duration (hr)	Corrosion-Product Concentration in Salt Samples ^a (mole %)		
	V	Fe	Mo	Cr	Al	Ni		Sample H	Sample C	Other
								Vanadium Concentration		
OR 30-10	2.73		10.8			bal	500	<0.005	<0.005	<0.005
OR 30-20	5.11		10.8			bal	500	0.0274	0.0274	0.0261
OR 30-20	5.11		10.8			bal	1000	0.0198	0.0194	b
								Iron Concentration		
OR 30-11		4.12	10.8			bal	500	0.0146	0.0134	0.0152
OR 30-33		5.56	9.7	5.9	1.6	bal	1000	0.00517	0.00387	0.00517

^aSample designation "H" and "C" are discussed on page 13; "other" designates samples obtained from metallographic specimens.

^bNot determined.




Fig. 10. Attack at Hot-Leg Surface of Ternary Nickel-Molybdenum Alloy Containing 5.11 at. % V. Alloy was exposed to Salt 107 for 1000 hr. Heat OR 30-20.

chromium and aluminum in this latter test served to inhibit the reaction with iron.

Metallographic Results

Metallographic examinations of specimens from the 500-hr loop showed no evidence of attack other than light surface roughening. Examinations of the 1000-hr test, as indicated in Fig. 7, showed corrosive attack to a depth of 0.003 in. in the form of small subsurface voids.

Niobium

Corrosion-Product Concentrations

Loop tests of 500- and 1000-hr durations were carried out with ternary alloys containing 2.20 and 3.62 at. % Nb, respectively. As shown in Table 10, the niobium concentrations in salts exposed to these alloys increased from a value near 0.015 mole % in the 500-hr tests to values of from 0.022 to 0.025 mole % in the 1000-hr tests. Salts tested with

Table 10. Corrosion-Product Concentrations of Salts Tested with Nickel-Molybdenum-Niobium Alloys

Heat Number	Alloy Composition (at. %)			Test Duration (hr)	Niobium Concentration in Salt Samples ^a (mole %)		
	Nb	Mo	Ni		Sample H	Sample C	Other
OR 30-12	2.20	11.1	bal	500	0.00363	b	0.0135
OR 30-12	2.20	11.1	bal	1000	0.0225	0.0207	0.0233
OR 30-21	3.62	10.9	bal	500	0.0155	0.0174	0.0153
OR 30-21	3.62	10.9	bal	1000	0.0244	0.0228	0.0259

^aSample designations "H" and "C" are discussed on page 13; "other" designates samples obtained from metallographic specimens.

^bNot determined.

alloys which contained niobium combined with other additions showed very much lower niobium concentrations than did the simple ternary alloys. As seen in Table 11, concentrations in the multiple-addition tests were less than 0.002 mole % for niobium contents as high as 3.62 at. %. Thus, it appears that corrosion products formed by reactions with other components in these alloys, namely titanium, aluminum, and chromium, were effective in inhibiting reaction of the salt with niobium.

Metallographic Results

Neither ternary alloy containing niobium showed significant attack in metallographic examinations of 500-hr tests; however, the presence of very small subsurface voids to depths of approximately 0.001 in. was detected in examinations of the 1000-hr tests, as illustrated in Fig. 11. Corrosion results determined for alloys containing niobium together with other additions are summarized in Fig. 7. Except where aluminum and chromium were both present, attack in these alloys was less than 0.002 in. in depth.

Table 11. Corrosion-Product Concentrations of Salts Tested with Nickel-Molybdenum Alloys Containing Niobium in Combination with Other Alloying Elements

Heat Number	Alloy Composition (at. %)		Test Duration (hr)	Niobium Concentration in Salt Samples ^a (mole %)		
	Nb	Other Components		Sample H	Sample C	Other
OR 30-22	0.39	10.0 Mo, 6.6 Cr, 2.6 Al, bal Ni	500	0.00129	0.00181	0.00207
OR 30-22	0.39	10.0 Mo, 6.6 Cr, 2.6 Al, bal Ni	1000	0.00052	0.00104	0.00052
B2898	0.90	13.2 Mo, 3.24 Ti, bal Ni	500	<0.0005	<0.0005	b
B2897	0.92	13.8 Mo, 1.7 Ti, bal Ni	1000	0.00104	0.00052	0.00129
B3276	1.48	14.0 Mo, 9.3 Cr, bal Ni	500	0.00078	0.00052	0.00078
B3277	1.57	14.2 Mo, 9.5 Cr, 3.1 Al, bal Ni	500	<0.0005	<0.0005	<0.0005
B3277	1.57	14.2 Mo, 9.5 Cr, 3.1 Al, bal Ni	1000	0.00259	0.00181	0.00104
S T23013	3.23	10.4 Mo, 1.4 Al, 1.8 W, bal Ni	500	<0.0005	<0.0005	<0.0005

^aSample designations "H" and "C" are discussed on page 13; "other" designates samples obtained from metallographic specimens.

^bNot determined.

Tungsten

Corrosion-Product Concentrations

Single alloying additions of tungsten to the nickel-molybdenum system were evaluated at levels of 0.72 and 1.44 at. %, respectively. Loop tests of both alloys were conducted for 500 hr, at which time tungsten concentrations in the salt mixtures had reached levels of 0.029 to 0.032 mole %. In 500-hr tests of two alloys which contained tungsten in addition to chromium, niobium, or aluminum, the concentration of tungsten detected in salt samples was below 0.010 mole %. Compositions of these alloys and their attendant salt corrosion-product concentrations are shown in Table 12.



Fig. 11. Appearance of Voids in Nickel-Molybdenum Alloy Containing 3.62 at. % Nb after 1000-hr Exposure to Salt 107. Heat OR 30-21.

Table 12. Corrosion-Product Concentrations of Salts Tested with Nickel-Molybdenum Alloys Containing Tungsten

Heat Number	Alloy Composition (at. %)		Test Duration (hr)	Tungsten Concentration in Salt Samples ^a (mole %)		
	W	Other Components		Sample H	Sample C	Other
OR 30-9	0.72	11.2 Mo, bal Ni	500	0.0318	0.0287	0.0325
OR 30-19	1.44	11.4 Mo, bal Ni	500	0.0384	0.0311	0.0310
S T23011	1.72	10.2 Mo, 1.3 Al, 2.9 Nb, 4.8 Cr, bal Ni	500	0.00500	0.00983	b
S T23013	1.85	10.4 Mo, 1.4 Al, bal Ni	500	0.00223	0.00105	b

^aSamples designations "H" and "C" are discussed on page 13; "other" designates samples obtained from metallographic specimens.

^bNot determined.

Metallographic Results


Metallographic examination of loops constructed of nickel-molybdenum-tungsten alloys revealed only slight surface pitting, as illustrated in Fig. 12. The addition of aluminum together with tungsten led to heavy surface pitting, while the addition of aluminum, chromium, and niobium produced subsurface voids to a depth of 0.0025 in., as shown in Fig. 7.



Fig. 12. Hot-Leg Surface of Nickel-Molybdenum Alloy Containing 1.44 at. % W after 500-hr Exposure to Salt 107. Heat OR 30-19.

Relative Thermodynamic Stabilities of Alloying Constituents

Since the salt mixtures supplied for this investigation were very uniform in composition, one can presume that the same relative activities of UF_4 and UF_3 existed at the start of each test. It follows, therefore, that the relative extent of reaction which occurred between the salt mixtures and an alloying element



for which

$$K_{\alpha} = \frac{\alpha_{M_x F_y} \cdot \alpha_{UF_4}^y}{\alpha_M^x \cdot \alpha_{UF_3}^y} \quad (12)$$

should be directly related to the activity of the fluoride compounds, $M_x F_y$, involving that element.

An indication of the relative activities of these compounds is provided by a consideration of their standard free energies of formation, as derived from the reaction



where

$$\alpha_{M_x F_y} = e^{-\frac{\Delta G_T^{\circ}}{RT}}$$

In Table 13 are listed the standard free energies of formation, per gram-atom of fluorine, of fluoride compounds at 800 and 600°C associated with each of the alloying elements investigated. Values are given for the most stable compounds (that is, those with most negative free energies) reported¹⁸ for these elements, and are listed in order of decreasing stabilities. The resultant order suggests that corrosion-product concentrations associated with each element at a given activity should have increased in the following order: W, Nb, Fe, Cr, V, Ti, and Al.

In Fig. 13, the general ranges of corrosion-product concentrations actually observed for these components, when present as single alloying additions, are plotted as a function of alloy content. It is seen that,

¹⁸A. Glassner, The Thermodynamic Properties of the Oxides, Fluorides, and Chlorides to 2500°K, ANL-5750.

Table 13. Relative Thermodynamic Stabilities of Fluoride Compounds Formed by Elements Employed as Alloying Additions (Data Compiled by Glassner)^a

Element	Most Stable Fluoride Compound	$\Delta G_{800^\circ\text{C}}^\circ$ ($\frac{\text{Kcal}}{\text{g atom of F}}$)	$\Delta G_{800^\circ\text{C}}^\circ$ ($\frac{\text{Kcal}}{\text{g atom of F}}$)
Al	AlF ₃	-87	-92
Ti	TiF ₃	-85	-90
V	VF ₂	-80	-84
Cr	CrF ₂	-72	-77
Fe	FeF ₂	-66	-66
Nb	NbF ₅	-58	-60
W	WF ₅	-46	-48

^aA. Glassner, The Thermodynamic Properties of the Oxides, Fluorides, and Chlorides to 2500°K, ANL-5750.

with the exception of niobium and tungsten, the concentrations per atomic per cent of addition do increase in the exact order predicted. Only tungsten noticeably deviates from this predicted behavior; the causes for this deviation have not been established, although the number of tests completed on alloys with tungsten additions were quite limited.

General Discussion of Alloying Effects

The corrosion-product concentrations associated with either iron, niobium, or tungsten alloying additions were much lower when these elements existed in multicomponent alloys than in simple ternary alloys. The reason for this behavior is undoubtedly associated with the presence of the more reactive alloying additions in the multicomponent alloys. Consider, for example, a system containing comparable additions of chromium and iron, for which the corrosion reactions are






Fig. 13. Comparison of Corrosion-Product Concentrations Formed in Salt 107 by Various Alloying Additions as a Function of Alloy Content.

Since ΔG_I is considerably more negative than ΔG_{II} , the equilibrium UF_3 concentration produced by the first reaction is higher than that which would be produced by the second reaction. According to the law of mass action, therefore, the FeF_2 concentration at equilibrium should be reduced in the presence of chromium compared to a system containing iron only.

While this means of corrosion inhibition was effective for those alloying components less reactive than chromium, its effect was not apparent among elements of relatively high reactivities. Thus, chromium corrosion-product concentrations were the same in the case of alloys containing both aluminum and chromium as in the case of alloys containing chromium alone. Similarly, the presence of aluminum did not noticeably reduce the titanium-corrosion products associated with titanium-containing alloys. For most of the multicomponent alloys, the amount of chromium and titanium, on an atomic percent basis, exceeded that of aluminum; consequently their activities could have approached the activity of the aluminum component. Nevertheless, the high aluminum concentrations of fluoride mixtures after these tests suggest a level of UF_3 higher than would have been produced by either chromium or titanium alone, so that some inhibitive action would be predicted. The fact that none occurred may suggest that the measured aluminum concentrations were somewhat higher than actually existed.¹⁹

SUMMARY AND CONCLUSIONS

The corrosion properties of solid-solution alloying elements in the Ni-17% Mo system were investigated in molten mixtures of NaF-LiF-KF- UF_4 (11.2-41.0-45.3-2.5 mole %). The corrosion susceptibility of alloying additions was found to increase in the following order: Fe, Nb, V, Cr, W, Ti, and Al. With the exception of tungsten, the susceptibility of

¹⁹Considerable difficulty was in fact encountered in analyses of this element by wet chemical methods. Analyses of a limited number of samples were consequently made using semiquantitative spectrographic techniques. Concentrations obtained by the latter technique were lower by a factor of approximately 2/3 than the values that were reported in Tables 6 and 7.

these elements to corrosion increased in approximately the same order as the stabilities of fluoride compounds of the elements.

The corrosion-product concentrations produced by either iron, niobium or tungsten alloying additions in the above salt mixture were much lower when these elements existed in combination with chromium, titanium, or aluminum than when they existed as single alloying additions. In contrast, corrosion-product concentrations associated with chromium, titanium, or aluminum were unchanged by the presence of other alloying constituents.

The metallographic examinations of all alloys investigated under this program showed considerably less corrosion than Inconel under equivalent conditions. Surface roughening or shallow pitting was manifested in hot-leg sections of all the loops tested. Shallow subsurface voids were also seen in aluminum- and niobium-containing systems. Alloys containing more than one alloying addition invariably were attacked to depths greater than alloys containing each of the additions individually. The greatest depths of attack, which ranged from 0.003 to 0.0045 in. in 1000-hr exposures, were incurred in alloys which contained combined additions of aluminum and chromium or aluminum and titanium. Alloys without either aluminum or titanium in no case exhibited attack to depths of more than 0.002 in. and generally showed attack in the range from 0.001 to 0.002 in.

In the case of the majority of alloys tested, the depth of attack increased at a greater rate between 0 and 500 hr than between 500 and 1000 hr. This finding is in agreement with the concentrations of corrosion products, which in general increased only slightly between the periods of 500 and 1000 hr. Both results suggest that nearly steady-state conditions were established within the first 500 hr of test operation.

In view of the generally favorable results of these tests, one has considerable freedom in the choice of potential alloying components for nickel-molybdenum alloys for molten salt service. Only titanium and aluminum appear to afford potential corrosion problems, particularly if used as combined additions or in combination with chromium. Thus, the choice of an optimum alloy composition for any given application can be judged mainly on the basis of strength and fabrication requirement.

ACKNOWLEDGMENTS

The many loop experiments reported here were carried out under the skilled hand of M. A. Redden. The author is also indebted to W. O. Harms for his editorial assistance and guidance as thesis advisor.

INTERNAL DISTRIBUTION

1-3.	Central Research Library	58.	C. W. Collins
4-5.	ORNL Y-12 Technical Library	59.	E. L. Compere
	Document Reference Section	60.	K. V. Cook
6-15.	Laboratory Records	61.	W. H. Cook
16.	Laboratory Records, ORNL-RC	62.	L. T. Corbin
17.	ORNL Patent Office	63.	B. Cox
18.	R. K. Adams	64.	J. L. Crowley
19.	G. M. Adamson	65.	F. L. Culler
20.	R. G. Affel	66.	D. R. Cuneo
21.	J. L. Anderson	67.	J. E. Cunningham
22.	R. F. Apple	68.	J. M. Dale
23.	C. F. Baes	69.	D. G. Davis
24.	J. M. Baker	70.	R. J. DeBakker
25.	S. J. Ball	71-80.	J. H. DeVan
26.	C. E. Bamberger	81.	S. J. Ditto
27.	C. J. Barton	82.	A. S. Dworkin
28.	H. F. Bauman	83.	I. T. Dudley
29.	S. E. Beall	84.	D. A. Dyslin
30.	R. L. Beatty	85.	W. P. Eatherly
31.	M. J. Bell	86.	J. R. Engel
32.	M. Bender	87.	E. P. Epler
33.	C. E. Bettis	88.	R. B. Evans III
34.	E. S. Bettis	89.	D. E. Ferguson
35.	D. S. Billington	90.	L. M. Ferris
36.	R. E. Blanco	91.	A. P. Fraas
37.	F. F. Blankenship	92.	H. A. Friedman
38.	J. O. Blomeke	93.	J. H. Frye, Jr.
39.	R. Blumberg	94.	W. K. Furlong
40.	E. G. Bohlmann	95.	C. H. Gabbard
41.	C. J. Borkowski	96.	R. B. Gallaher
42.	G. E. Boyd	97.	R. E. Gehlbach
43.	J. Braunstein	98.	J. H. Gibbons
44.	M. A. Bredig	99.	L. O. Gilpatrick
45.	R. B. Briggs	100.	W. R. Grimes
46.	H. R. Bronstein	101.	A. G. Grindell
47.	G. D. Brunton	102.	R. W. Gunkel
48.	D. A. Canonico	103.	R. H. Guymon
49.	S. Cantor	104.	J. P. Hammond
50.	W. L. Carter	105.	B. A. Hannaford
51.	G. I. Cathers	106.	P. H. Harley
52.	O. B. Cavin	107.	D. G. Harman
53.	A. Cepolina	108.	W. O. Harms
54.	J. M. Chandler	109.	C. S. Harrill
55.	F. H. Clark	110.	P. N. Haubenreich
56.	W. R. Cobb	111.	R. E. Helms
57.	H. D. Cochran	112.	P. G. Herndon

113. D. N. Hess
114. J. R. Hightower
115-117. M. R. Hill
118. H. W. Hoffman
119. D. K. Holmes
120. P. P. Holz
121. R. W. Horton
122. A. Houtzeel
123. T. L. Hudson
124. W. R. Huntley
125. H. Inouye
126. W. H. Jordan
127. P. R. Kasten
128. R. J. Kedl
129. M. T. Kelley
130. M. J. Kelly
131. C. R. Kennedy
132. T. W. Kerlin
133. H. T. Kerr
134. J. J. Keyes
135. D. V. Kiplinger
136. S. S. Kirslis
137. J. W. Koger
138. R. B. Korsmeyer
139. A. I. Krakoviak
140. T. S. Kress
141. J. W. Krewson
142. C. E. Lamb
143. J. A. Lane
144. C. E. Larson
145. J. J. Lawrence
146. M. S. Lin
147. R. B. Lindauer
148. A. P. Litman
149. G. H. Llewellyn
150. E. L. Long, Jr.
151. A. L. Lotts
152. M. I. Lundin
153. R. N. Lyon
154. R. L. Macklin
155. H. G. MacPherson
156. R. E. MacPherson
157. J. C. Mailen
158. D. L. Manning
159. C. D. Martin
160. W. R. Martin
161. H. V. Mateer
162. T. H. Mauney
163. H. McClain
164. R. W. McClung
165. H. E. McCoy
166. D. L. McElroy
167. C. K. McGlothlan
168. C. J. McHargue
169. L. E. McNeese
170. J. R. McWherter
171. H. J. Metz
172. A. S. Meyer
173. R. L. Moore
174. D. M. Moulton
175. T. W. Mueller
176. H. A. Nelms
177. H. H. Nichol
178. J. P. Nichols
179. E. L. Nicholson
180. L. C. Oakes
181. P. Patriarca
182. A. M. Perry
183. T. W. Pickel
184. H. E. Piper
185. B. E. Prince
186. G. L. Ragan
187. J. L. Redford
188. M. Richardson
189. G. D. Robbins
190. R. C. Robertson
191. K. A. Romberger
192. R. C. Ross
193. H. C. Savage
194. W. F. Schaffer
195. C. E. Schilling
196. Dunlap Scott
197. J. L. Scott
198. H. E. Seagren
199. C. E. Sessions
200. J. H. Shaffer
201. W. H. Sides
202. G. M. Slaughter
203. A. N. Smith
204. F. J. Smith
205. G. P. Smith
206. O. L. Smith
207. P. G. Smith
208. I. Spiewak
209. R. C. Steffy
210. W. C. Stoddart
211. H. H. Stone
212. R. A. Strehlow
213. D. A. Sundberg
214. J. R. Tallackson
215. E. H. Taylor
216. W. Terry
217. R. E. Thoma
218. P. F. Thomason

- | | | | |
|------|----------------|------|------------------|
| 219. | L. M. Toth | 230. | K. W. West |
| 220. | D. B. Trauger | 231. | M. E. Whatley |
| 221. | W. E. Unger | 232. | J. C. White |
| 222. | G. M. Watson | 233. | R. P. Wichner |
| 223. | J. S. Watson | 234. | L. V. Wilson |
| 224. | H. L. Watts | 235. | Gale Young |
| 225. | C. F. Weaver | 236. | H. C. Young |
| 226. | B. H. Webster | 237. | J. P. Young |
| 227. | A. M. Weinberg | 238. | E. L. Youngblood |
| 228. | J. R. Weir | 239. | F. C. Zapp |
| 229. | W. J. Werner | | |

EXTERNAL DISTRIBUTION

- 240. G. G. Allaria, Atomics International
- 241. J. G. Asquith, Atomics International
- 242. D. F. Cope, RDT, SSR, AEC, Oak Ridge National Laboratory
- 243. C. B. Deering, AEC, OSR, Oak Ridge National Laboratory
- 244. H. M. Dieckamp, Atomics International
- 245. A. Giambusso, AEC, Washington
- 246. F. D. Haines, AEC, Washington
- 247. C. E. Johnson, AEC, Washington
- 248. W. L. Kitterman, AEC, Washington
- 249. W. J. Larkin, AEC, Oak Ridge Operations
- 250-251. T. W. McIntosh, AEC, Washington
- 252. A. B. Martin, Atomics International
- 253. D. G. Mason, Atomics International
- 254. G. W. Meyers, Atomics International
- 255. D. E. Reardon, AEC, Canoga Park Area Office
- 256. H. M. Roth, AEC, Oak Ridge Operations
- 257. M. Shaw, AEC, Washington
- 258. J. M. Simmons, AEC, Washington
- 259. W. L. Smalley, AEC, Washington
- 260. S. R. Stamp, AEC, Canoga Park Area Office
- 261. E. E. Stansbury, the University of Tennessee
- 262. R. F. Sweek, AEC, Washington
- 263. A. Taboada, AEC, Washington
- 264. R. F. Wilson, Atomics International
- 265. Laboratory and University Division, AEC, Oak Ridge Operations
- 266-280. Division of Technical Information Extension