


OAK RIDGE NATIONAL LABORATORY
operated by
UNION CARBIDE CORPORATION
NUCLEAR DIVISION
for the
U.S. ATOMIC ENERGY COMMISSION



ORNL - TM - 2596

Copy No. - 33

Date - July, 8, 1969

FRACTIONAL CRYSTALLIZATION REACTIONS IN THE SYSTEM $\text{LiF}-\text{BeF}_2-\text{ThF}_4$

R. E. Thoma and J. E. Ricci¹

ABSTRACT

Equilibrium and non-equilibrium crystallization reactions in the system $\text{LiF}-\text{BeF}_2-\text{ThF}_4$ are analyzed in relation to their potential application to molten salt reactor fuel reprocessing. Heterogeneous equilibria in the temperature range from the liquidus at 590°C to the solidus at 350°C are described quantitatively and in detail by means of ten typical isothermal sections and by three temperature-composition sections. The implications of metastable fractionation in this temperature interval are discussed as a possible feed control step in reductive extraction reprocessing of molten salt breeder reactor fuels.

NOTICE This document contains information of a preliminary nature and was prepared primarily for internal use at the Oak Ridge National Laboratory. It is subject to revision or correction and therefore does not represent a final report.

DISTRIBUTION OF THIS DOCUMENT IS UNLIMITED

RECEIVED BY DTIE JUL 23 1969

1504p

LEGAL NOTICE

This report was prepared as an account of Government sponsored work. Neither the United States, nor the Commission, nor any person acting on behalf of the Commission:

- A. Makes any warranty or representation, expressed or implied, with respect to the accuracy, completeness, or usefulness of the information contained in this report, or that the use of any information, apparatus, method, or process disclosed in this report may not infringe privately owned rights; or
- B. Assumes any liabilities with respect to the use of, or for damages resulting from the use of any information, apparatus, method, or process disclosed in this report.

As used in the above, "person acting on behalf of the Commission" includes any employee or contractor of the Commission, or employee of such contractor, to the extent that such employee or contractor of the Commission, or employee of such contractor prepares, disseminates, or provides access to, any information pursuant to his employment or contract with the Commission, or his employment with such contractor.

CONTENTS

	Page
Abstract	1
Introduction	4
Liquid-Solid Phase Reactions In The System $\text{LiF}-\text{BeF}_2-\text{ThF}_4$	5
Potential Application of Fractional Crystallization In Chemical Reprocessing	24

LEGAL NOTICE

This report was prepared as an account of Government sponsored work. Neither the United States, nor the Commission, nor any person acting on behalf of the Commission:

A. Makes any warranty or representation, expressed or implied, with respect to the accuracy, completeness, or usefulness of the information contained in this report, or that the use of any information, apparatus, method, or process disclosed in this report may not infringe privately owned rights; or

B. Assumes any liabilities with respect to the use of, or for damages resulting from the use of any information, apparatus, method, or process disclosed in this report.

As used in the above, "person acting on behalf of the Commission" includes any employee or contractor of the Commission, or employee of such contractor, to the extent that such employee or contractor of the Commission, or employee of such contractor prepares, disseminates, or provides access to, any information pursuant to his employment or contract with the Commission, or his employment with such contractor.

INTRODUCTION

The ORNL Molten Salt Reactor Program is devoted to the development of molten salt breeder reactors which employ mixtures of molten fluorides as core fluids. Until recently, the most promising approach to the development of molten salt breeder reactors appeared to be a two-region reactor with fissile and fertile materials in separate fuel and blanket streams. Thorium would be carried in the blanket salt, in a salt stream which would consist of a ${}^7\text{LiF}-\text{BeF}_2-\text{ThF}_4$ mixture. Advances in chemical reprocessing have provided evidence recently that ${}^{233}\text{Pa}$ and possibly the rare earth fission products can be separated from mixed thorium-uranium salt by reductive extraction methods employing liquid bismuth. This development, along with other design developments, makes possible a single-fluid breeder reactor, one which has greater simplicity and reliability than the two-fluid reactor. The fuel for the single fluid reactor would be composed of ${}^7\text{LiF}$, BeF_2 , ThF_4 , and ${}^{233}\text{UF}_4$, and might be expected to contain ~ 12 mole % ThF_4 . Optimization of the ${}^7\text{LiF}$ and BeF_2 concentrations is not complete, because the trade-off values of several significant factors have not yet been established. These include selection limitations imposed by the equilibrium phase behavior of the $\text{LiF}-\text{BeF}_2-\text{ThF}_4$ system (${}^{233}\text{UF}_4$ concentration will be only 0.2 mole %, and is therefore of little consequence in this connection), physical properties such as viscosity, vapor pressure, thermal conductivity, and the relations of $\text{LiF}-\text{BeF}_2-\text{ThF}_4$ composition to the development of chemical processes for removal of protactinium and the lanthanides.

Effective separation of the rare earth fission products from fluoride salt streams which contain thorium fluoride is the keystone to development of semi-continuous reprocessing in single-fluid molten salt reactors. Several methods for reprocessing spent $\text{LiF}-\text{BeF}_2-\text{ThF}_4-\text{UF}_4$ fuels are currently under investigation. The method which is regarded as most tractable for engineering development involves the selective chemical reduction of the various components into liquid bismuth solutions at about 600°C , utilizing multistage countercurrent extraction operations. The current status of engineering development of this process has been described by Whatley et al.² The initial steps remove uranium and protactinium by reductive extraction.³ A strong incentive then exists to remove the rare-earth fission products from the remaining salt. The most nearly feasible approach to this separation seems to be their extraction

into bismuth alloy,³ even though the recycle volumes of extractant are marginally acceptable. The efficiency of this separation step would be greatly enhanced if the concentration of the rare earths in the salt mixture were increased by at least tenfold, and if the residual salt solutions were of a much lower concentration of thorium fluoride. That the LiF-BeF₂-ThF₄ phase diagram⁴ shows the occurrence of low melting mixtures of low thorium fluoride content which are producible from MSBR single-core fluids by metastable crystallization has suggested the possibility that non-equilibrium fractionation reactions might be exploited as a feed control step in the reductive extraction process.

Because of its relative complexity, the unpublished version of the LiF-BeF₂-ThF₄ phase diagram may experience less frequent or less effective application in molten salt reactor technology than is warranted by the developments cited above. We therefore describe in this report further detailed aspects of equilibrium and non-equilibrium behavior in the system.

LIQUID-SOLID PHASE REACTIONS IN THE SYSTEM LiF-BeF₂-ThF₄

Methods for interpreting polythermal and isothermal phase diagrams are described extensively in an earlier report⁵ where the phase relationships in a number of fluoride systems were analyzed in detail. Interpretation of the equilibrium behavior in the system LiF-BeF₂-ThF₄⁴ (Figure 1) is somewhat more complex than for the systems analyzed because of the occurrence of an unusual solid solution which is produced as the compound 3LiF·ThF₄ crystallizes from LiF-BeF₂-ThF₄ melts. The crystal phase of nominal composition, 3LiF·ThF₄, precipitates as a ternary solid solution which, at its maximum in composition variability (near the solidus), is described by a composition triangle with apices at LiF-ThF₄ (75-25 mole %), LiF-BeF₂-ThF₄ (58-16-26 mole %), and LiF-BeF₂-ThF₄ (59-20-21 mole %). Two substitution models may provide an explanation for the single phase solid solution area: (1) a substitution of one Be²⁺ ion for a Li⁺ ion with the simultaneous formation of a Th⁴⁺ vacancy for every four Be²⁺ ions substituted for Li⁺ ions to provide electroneutrality and (2) substitution of a single Be²⁺ ion for a Li⁺ ion with the simultaneous formation of a Li⁺ vacancy. Model (1) would afford a solid solution





Fig. 1. Polythermal Projection of the LiF-BeF₂-ThF₄ Equilibrium Phase Diagram.

limit in good agreement with the leg of the triangular area with the lesser ThF_4 content whereas model (2) would give a line extending from $3\text{LiF}\cdot\text{ThF}_4$ toward $\text{BeF}_2\text{-ThF}_4$ (60-40 mole %). This is a limiting line which permits considerably higher ThF_4 content than that found experimentally. Accordingly, it appears that both models are simultaneously applicable for the crystallization behavior of $3\text{LiF}\cdot\text{ThF}_4$ as it crystallizes from $\text{LiF-BeF}_2\text{-ThF}_4$ melts. Once the crystal structure of $3\text{LiF}\cdot\text{ThF}_4$ has been established (a study of the structure is currently in progress⁶) it will be possible to appraise the validity of these models.

Application of ternary phase diagrams to technology often requires a knowledge of the identities and compositions of the various phases in equilibrium at specific temperatures. Such information is represented by equilibrium phase diagrams. Typically, phase diagrams of ternary systems are presented as projections of temperature-composition prisms on their basal planes. When such schematic representation includes liquidus temperatures, equilibrium crystallization and melting reactions can be described in a quantitative manner. Here, the use of isothermal sections is often valuable, particularly if the phase diagram is complex. The chief feature of the isothermal section is that it provides information both about the identity and relative masses of coexisting phases.

The crystallization behavior of the $3\text{LiF}\cdot\text{ThF}_4$ ternary solid solution determines the composition sequence as $\text{LiF-BeF}_2\text{-ThF}_4$ melts are cooled. A series of equilibrium isotherms is shown in Figs. 2 to 11, which describe all the equilibrium reactions in the temperature interval from 590°C to 350°C , i.e., the liquidus-solidus interval of chief relevance to the compositions which are likely to have application in molten salt reactor technology, and in which all $3\text{LiF}\cdot\text{ThF}_4$ solid solution melting-freezing reactions occur. Within this interval all the solid phases of the system are involved. The equilibrium behavior of chief importance to us is described further by the temperature-composition sections, $3\text{LiF}\cdot\text{ThF}_4\text{-2LiF}\cdot\text{BeF}_2$, $\text{LiF}\cdot\text{ThF}_4\text{-2LiF}\cdot\text{BeF}_2$, and $\text{LiF}\cdot 2\text{ThF}_4\text{-2LiF}\cdot\text{BeF}_2$, shown in Figs. 12-14 (schematic, not to scale).






Fig. 3. Isothermal Section of the System LiF-BeF₂-ThF₄ at 570°C.





Fig. 4. Isothermal Section of the System LiF-BeF₂-ThF₄ at 562⁰C.



11

Fig. 5. Isothermal Section of the System LiF-BeF₂-ThF₄ at 490°C.




Fig. 6. Isothermal Section of the System LiF-BeF₂-ThF₄ at 457°C.





Fig. 7. Isothermal Section of the System LiF-BeF₂-ThF₄ at 447°C.



14

Fig. 8. Isothermal Section of the System LiF-BeF₂-ThF₄ at 440°C.





Fig. 9. Isothermal Section of the System LiF-BeF₂-ThF₄ at 430°C.

Fig. 10. Isothermal Section of the System LiF-BeF₂-ThF₄ at 430°C.




Fig. 11. Isothermal Section of the System LiF-BeF₂-ThF₄ at 350°C.

The isothermal sections included in Figs. 2 to 11 are drawn to scale and represent the experimental results which were the basis of the previously published phase diagram.⁴ Composition-temperature relations in the LiF-BeF₂-ThF₄ system for LiF concentrations greater than 50 mole % are shown in detail in Fig. 15.

The straight lines appearing in Figs. 2 to 11 are tie-lines (or "conodes") connecting two phases which are in equilibrium. In Fig. 16, point P, as a point on such a tie-line joining points b and z, represents a mixture of the phases (or compositions) b and z with the mole fraction of b equal to the ratio of line lengths zP/zb.

In the case of a mixture of three phases, such as the points a, b, c making up the total composition at point P (Fig. 16), the relative amounts of the phases a, b, c making up P may be determined as follows, with the three fractions defined as x of a, y of b, 1-x-y of c. Then:

(1) Graphically: extend the line bP to fix the point z on the line ac. Then $y = zP/zb$, and $x = (zc/ac)(1-y)$.

(2) Analytically: let the fractions of the components A and B at each of the four points (a, b, c, P) be

$$\begin{array}{cccc} A_a & A_b & A_c & A_p \\ B_a & B_b & B_c & B_p \end{array}$$

Then by similar triangles, we have

$$\frac{B_a - B_z}{A_a - A_z} = \frac{B_a - B_c}{A_a - A_c} = \alpha$$

$$\frac{B_b - B_z}{A_b - A_z} = \frac{B_b - B_p}{A_b - A_p} = \beta$$


$$\text{Then } B_z = B_b - \beta A_b + \beta A_z = B_a - \alpha A_a + \alpha A_z$$

$$\text{Hence } A_z = \frac{(B_a - B_b) + \beta A_b - \alpha A_a}{\beta - \alpha}$$

$$B_z = B_b - \beta A_b + \beta(A_z).$$

$$\text{Then } y = \frac{B_p - B_z}{B_b - B_z}$$

$$\text{and } x = \frac{A_z - A_c}{A_a - A_c} (1 - y).$$

Fig. 12. The Section $3\text{LiF} \cdot \text{ThF}_4 - 2\text{LiF} \cdot \text{BeF}_2$

ORNL-DWG 69-5295




Fig. 13. The Section $LiF \cdot ThF_4 - 2LiF \cdot BeF_2$




Fig. 14. The Section $LiF \cdot 2ThF_4 - 2LiF \cdot BeF_2$




Fig. 15. Phase Diagram of the LiF-BeF₂-ThF₄ System for Compositions 50 - 100 mole % LiF.

ORNL DWG. 69-7559





Fig. 16. Schematic Drawing for Use in Calculating Relative Fractions of Coexisting Phases at Point P.

POTENTIAL APPLICATION OF FRACTIONAL CRYSTALLIZATION
IN CHEMICAL REPROCESSING

Under equilibrium conditions, the crystallization end-point in three component systems such as in the $\text{LiF}-\text{BeF}_2-\text{ThF}_4$ system, depends on the "compatibility" or three solid phase triangles of the equilibrium diagram. As an example, compositions in the triangle $\text{LiF} - 3\text{LiF}\cdot\text{ThF}_4 - 2\text{LiF}\cdot\text{BeF}_2$ have their crystallization end-point at the 444°C peritectic reaction point. As noted previously,⁷ dynamic crystallization of $\text{LiF}-\text{BeF}_2-\text{ThF}_4$ mixtures does not follow the equilibrium crystallization diagram exactly; instead, non-equilibrium crystallization proceeds characteristically by sub-cooling (i.e., delayed crystallization under dynamic cooling), and by incomplete recombination of liquid and solid phases at the peritectic reaction points. Thus, liquids are produced from mixtures which are of interest to us, primarily those containing high concentrations of LiF , which are richer in BeF_2 than their equilibrium counterparts, and which crystallize as described by the lower melting areas of the phase diagram. The consequence of non-equilibrium fractionation is thus to produce liquid residues which are lower in ThF_4 content than at equilibrium.

Let us examine the difference between equilibrium and non-equilibrium crystallization behavior of a liquid composition that would partially typify the reactions of MSBR salts. Suppose the composition c, $\text{LiF}-\text{BeF}_2-\text{ThF}_4$ (63-32-5 mole %), undergoes equilibrium crystallization. On complete solidification, the frozen salt will consist of the three crystalline phases, $3\text{LiF}\cdot\text{ThF}_4$ ss, $2\text{LiF}\cdot\text{BeF}_2$ and $\text{LiF}\cdot 2\text{ThF}_4$ in proportions given by the position of point c in the corresponding triangle of Figs. 9, 10, and 11.

For non-equilibrium crystallization this triangle has no significance. The non-equilibrium process consists of four consecutive steps, seen on the basis of the following diagram:



Step (1): freezing starts at $\sim 446^\circ\text{C}$ for composition c , and the liquid travels on the solid solution liquidus surface to reach curve $P_1 - P_3$ at some point ℓ (at $\sim 440^\circ\text{C}$), while precipitating some solid solution of composition between a and b , say a' as average.


Step (2): liquid travels on curve $P_1 - P_3$, to reach P_3 (433°C), while precipitating a mixture of solid solution (of composition between b and s , say b' as average) and $2\text{LiF} \cdot \text{BeF}_2$.

Step (3): liquid travels on curve $P_3 - E$, to reach E (356°) while precipitating mixture of $\text{LiF} \cdot 2\text{ThF}_4 + 2\text{LiF} \cdot \text{BeF}_2$.

Step (4): liquid at E (356°) freezes to mixture of $\text{LiF} \cdot 2\text{ThF}_4 + 2\text{LiF} \cdot \text{BeF}_2 + \text{BeF}_2$.

Quantities involved for 1 mole of starting composition c :

Step (1): draw straight line $a'c$ and extend it to curve P_1-P_3 , to fix point ℓ :




Moles of liquid reaching $\ell = \frac{a'c}{a'l} = m_1$;

Moles of ThF_4 precipitated (in step 1, or between 446 and 440°)

$$= x_a, (1-m_1) = p_1,$$

in which x_a = mole fraction of ThF_4 at a' , etc.

Step (2): draw straight line $b'-H$, and extend straight line ℓP_3 back to fix point y on line $b'-H$:




Moles of liquid reaching $P_3 = \frac{y_L}{y_{P_3}} (m_1) = m_2$;

Moles of ThF_4 precipitated (in step 2, or between 440° and 433°)

$$= x_D, \frac{y_H}{b'H} (m_1 - m_2) = p_2.$$

Step (3): draw straight line DH and extend straight line P_3E back to fix point z on the line DH:



Moles of liquid reaching E = $\frac{zP_3}{zE} (m_2) = m_3$;

Moles ThF_4 precipitated (in step 3, or between 433° and 356°)

$$= \frac{2}{3} \left(\frac{zH}{DH} \right) (m_2 - m_3) = p_3,$$

since $x_D = 2/3$.

Step (4): moles ThF_4 precipitated in this step (at 356°)


$$= x_c - (p_1 + p_2 + p_3).$$

Thus, given the original composition c on the phase diagram as we have it, one can make estimates regarding what happens in steps (1) and (2), and these estimates fix what happens in steps (3) and (4), for the

limit of non-equilibrium behavior. This means a process in which there is never any interaction between precipitated solid and solution. Actual behavior will of course be somewhere between this and the equilibrium process.

Since non-equilibrium fractionation of $\text{LiF}\cdot\text{BeF}_2\text{-ThF}_4$ melts produces final liquids which are low in thorium, and since the concentrations of rare earths in the solutions are expected to be about 20 ppm at the time when fuel processing is economically mandatory, one might anticipate that a semi-zone refining step might well produce and transport liquids of low thorium concentration and containing a relatively high concentration of rare earths (the solubility of the lanthanide trifluorides in any of the melts one might encounter is almost certainly to be at least 200 ppm at the low temperatures which would be present in this part of the feeder apparatus). The efficiency of this concentration step could possibly be impaired seriously if the rare earth trifluorides either formed intermediate compounds (such compounds are formed only for the lanthanides of $Z \geq 63$) which interacted with the crystallizing phases or otherwise formed solid solutions with any of the crystallizing phases. The structure of $2\text{LiF}\cdot\text{BeF}_2^8$ and $\text{LiF}\cdot\text{ThF}_4^9$ are known and believed to be incapable of serving as solid state hosts for the rare earth fluorides. The $3\text{LiF}\cdot\text{ThF}_4$ solid solution is an unknown factor in this consideration and could conceivably act as a solvent for lanthanide ions. This possibility as well as the possibility that $\text{LiF}\cdot 2\text{ThF}_4$ might also serve as a solid state solvent for lanthanide ions could be examined easily through a small scale laboratory program.

1. Consultant, Department of Chemistry, New York University, University Heights, New York.
2. M. E. Whatley et al., Nuclear Applications, (in press).
3. J. H. Shaffer and D. M. Moulton, Reductive Extraction Processing of MSBR Fuels, in Reactor Chemistry Division Annual Report for Period Ending February 28, 1968, ORNL-4396.
4. R. E. Thoma, H. Insley, H. A. Friedman, and C. F. Weaver, J. Phys. Chem. 64, 865 (1960).
5. J. E. Ricci, Guide to the Phase Diagrams of the Fluoride Systems, ORNL-2396, 1958.
6. G. D. Brunton, ORNL, Unpublished work, 1969.
7. C. F. Weaver, R. E. Thoma, H. Insley, and H. A. Friedman, Phase Equilibria in Molten Salt Breeder Reactor Fuels, I. The System LiF-BeF₂-UF₄-ThF₄, ORNL-2896, December, 1960.
8. J. H. Burns and E. K. Gordon, Acta Cryst. 20, 135 (1966).
9. G. D. Brunton, 21, 814 (1964).



DISTRIBUTION

1. R. K. Adams
2. G. M. Adamson
3. R. G. Affel
4. J. L. Anderson
5. R. F. Apple
6. C. F. Baes
7. J. M. Baker
8. S. J. Ball
9. C. E. Bamberger
10. C. J. Barton
11. H. F. Bauman
12. S. E. Beall
13. R. L. Beatty
14. M. J. Bell
15. M. Bender
16. C. E. Bettis
17. E. S. Bettis
18. D. S. Billington
19. R. E. Blanco
20. F. F. Blankenship
21. J. O. Blomeke
22. R. Blumberg
23. E. G. Bohlmann
24. C. J. Borkowski
25. G. E. Boyd
26. J. Braunstein
27. M. A. Bredig
28. R. B. Briggs
29. H. R. Bronstein
30. G. D. Brunton
31. D. A. Canonico
32. S. Cantor
33. D. W. Cardwell
34. W. L. Carter
35. G. I. Cathers
36. J. E. Caton
37. O. B. Cavin
38. J. M. Chandler
39. F. H. Clark
40. W. R. Cobb
41. H. E. Cochran
42. C. W. Collins
43. E. L. Compere
44. K. V. Cook
45. W. H. Cook
46. J. W. Cooke
47. L. T. Corbin
48. B. Cox
49. J. L. Crowley
50. F. L. Culler
51. D. R. Cuneo
52. J. M. Dale
53. D. G. Davis
54. R. J. DeBakker
55. J. H. DeVan
56. S. J. Ditto
57. A. S. Dworkin
58. I. T. Dudley
59. W. P. Eatherly
60. J. R. Engel
61. E. P. Epler
62. D. E. Ferguson
63. L. M. Ferris
64. A. P. Fraas
65. J. K. Franzreb
66. H. A. Friedman
67. D. N. Fry
68. J. H. Frye, Jr.
69. W. K. Furlong
70. C. H. Gabbard
71. R. B. Gallaher
72. R. E. Gehlbach
73. J. H. Gibbons
74. L. O. Gilpatrick
75. W. R. Grimes
76. A. G. Grindell
77. R. W. Gunkel
78. R. H. Guymon
79. J. P. Hammond
80. B. A. Hannaford
81. P. H. Harley
82. D. G. Harman
83. W. O. Harms
84. C. S. Harrill
85. P. N. Haubenreich
86. G. M. Hebert
87. R. E. Helms
88. P. G. Herndon
89. D. N. Hess
90. J. R. Hightower
91. M. R. Hill
92. H. W. Hoffman
93. D. K. Holmes
94. P. P. Holz
95. R. W. Horton
96. A. Houtzeel
97. T. L. Hudson
98. W. R. Huntley

DISTRIBUTION

99. H. Inouye
100. W. H. Jordan
101. P. R. Kasten
102. R. J. Kedl
103. M. T. Kelley
104. M. J. Kelley
105. C. R. Kennedy
106. T. W. Kerlin
107. H. T. Kerr
108. J. J. Keyes
109. D. V. Kiplinger
110. S. S. Kirslis
111. J. W. Koger
112. R. B. Korsmeyer
113. A. I. Krakoviak
114. T. S. Kress
115. J. W. Krewson
116. C. E. Lamb
117. J. A. Lane
118. J. J. Lawrence
119. M. S. Lin
120. R. B. Lindauer
121. A. P. Litman
122. E. L. Long
123. A. L. Lotts
124. M. I. Lundin
125. R. N. Lyon
126. R. L. Macklin
127. H. G. MacPherson
128. R. E. MacPherson
129. J. C. Mailen
130. D. L. Manning
131. C. D. Martin
132. W. R. Martin
133. H. V. Mateer
134. C. Matthews
135. T. H. Mauney
136. R. W. McClung
137. H. E. McCoy
138. D. L. McElroy
139. C. K. McGlothlan
140. C. J. McHargue
141. H. A. McLain
142. L. E. McNeese
143. J. R. McWherter
144. H. J. Metz
145. A. S. Meyer
146. R. L. Moore
147. D. M. Moulton
148. T. R. Mueller
149. H. H. Nichol
150. J. P. Nichols
151. E. L. Nicholson
152. L. C. Oakes
153. P. Patriarca
154. A. M. Perry
155. T. W. Pickel
156. H. B. Piper
157. B. E. Prince
158. G. L. Ragan
159. J. L. Redford
160. M. Richardson
161. G. D. Robbins
162. R. C. Robertson
163. W. C. Robinson
164. K. A. Romberger
165-167. M. W. Rosenthal
168. R. G. Ross
169. H. C. Savage
170. W. F. Schaffer
171. C. E. Schilling
172. Dunlap Scott
173. J. L. Scott
174. H. E. Seagren
175. C. E. Sessions
176. J. H. Shaffer
177. W. H. Sides
178. M. J. Skinner
179. G. M. Slaughter
180. A. N. Smith
181. F. J. Smith
182. G. P. Smith
183. O. L. Smith
184. P. G. Smith
185. I. Spiewak
186. R. C. Steffy
187. H. H. Stone
188. R. A. Strehlow
189. J. R. Tallackson
190. E. H. Taylor
191. W. Terry
192-201. R. E. Thoma
202. P. F. Thomason
203. L. M. Toth
204. D. B. Trauger
205. W. E. Unger
206. G. M. Watson
207. J. S. Watson

DISTRIBUTION

- 208. H. L. Watts
- 209. C. F. Weaver
- 210. B. H. Webster
- 211. A. M. Weinberg
- 212. J. R. Weir
- 213. W. J. Werner
- 214. K. W. West
- 215. M. E. Whatley
- 216. J. C. White
- 217. R. P. Wichner
- 218. L. V. Wilson
- 219. Gale Young
- 220. H. C. Young
- 221. J. P. Young
- 222. E. L. Youngblood
- 223. F. C. Zapp
- 224-225. Central Research Library
- 226-227. Document Reference Section
- 228-230. Laboratory Records
- 231. Laboratory Records (LRD-RC)

EXTERNAL DISTRIBUTION

- 232. C. B. Deering, AEC-OSR
- 233. A. Giambusso, AEC-Washington
- 234-235. T. W. McIntosh, AEC-Washington
- 236. H. M. Roth, AEC-ORO
- 237. M. Shaw, AEC-Washington
- 238. W. L. Smalley, AEC-ORO
- 239-253. Division of Technical Information Extension (DTIE)